
**Plastics piping and ducting systems —
Injection-moulded thermoplastics
fittings — Methods for visually assessing
the effects of heating**

*Systèmes de canalisations et de gaines en plastiques — Raccords
thermoplastiques moulés par injection — Méthodes d'essai pour
estimer visuellement les effets de la chaleur*



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

© ISO 2005

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 580 was prepared by Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, Subcommittee SC 5, *General properties of pipes, fittings and valves of plastic materials and their accessories — Test methods and basic specifications*.

This third edition cancels and replaces the second edition (ISO 580:1990), which has been technically revised.

Introduction

The test for determination of the resistance to heat according to the two test methods specified in this International Standard is applicable for distinguishing between properly and improperly moulded thermoplastics pipe fittings.

It can be used to

- determine whether cold slugs (pieces of material that enter the mould at a temperature significantly lower than the rest of the mass) or unfused areas are present,
- reveal cavities and porosity,
- determine the amount of moulded-in stress produced by the moulding process,
- reveal contamination, and
- show the integrity of the fusion line.

A stress-free part will generally have better properties and higher strength than parts with a higher degree of residual stress and will generally be less reactive when exposed to chemicals. By placing moulded fittings in a heated medium (air or liquid) at elevated temperature for a period of time dependant on their wall thickness, it is possible to detect internal stress.

Since the stresses start to be released as soon as the material passes to the rubbery state, it is only necessary to maintain the moulded pieces at a higher temperature for a defined period of time.

NOTE Injection-moulded fittings can be made by a number of techniques, whereby the material is injected into the mould cavity. These include single- or multi-point injection, diaphragm gating and ring gating. The technique used in the manufacture of mouldings will affect the way in which they are assessed.