



<b>AEROSPACE MATERIAL SPECIFICATION</b>	<b>AMS3281™</b>	<b>REV. F</b>
	Issued 1994-11 Revised 2016-03	
Superseding AMS3281E		
(R) Sealing Compound, Polysulfide (T) Synthetic Rubber for Integral Fuel Tank and Fuel Cell Cavities Low Density for Intermittent Use to 360 °F (182 °C)		

### RATIONALE

Changed adhesion promoter substrate requirements. Added a “no immersion” peel strength test. Increased maximum base viscosity requirement to 18000 poise (1800 Pa•s) to coincide with AMS3277. Removed Viscosity of Curing Agent requirement. Removed minimum swell requirement. Removed minimum flow requirement for Class B materials. Removed -80 °F storage life requirement for pre-mixed and frozen sealing compound to coincide with other polysulfide sealing compound requirements. Removed Chalking as a Initial Acceptance Test. Additional clarification to current requirements and editorial corrections were specified.

#### 1. SCOPE

##### 1.1 Form

This specification covers three types and three classes of fuel-resistant polysulfide sealing compound with low specific gravity, supplied as a two-component system which cures at room temperature.

##### 1.2 Application

This sealing compound has been used typically in sealing aircraft integral fuel tanks, fuel tank fillets and faying surfaces, pressure barriers and moldline surfaces, but usage is not limited to such applications. The sealing compound is resistant to jet fuels and is capable of withstanding long-term exposure from -65 to +250 °F (-54 to +121 °C) and short-term exposure (6 hours) to 360 °F (182 °C). AMS3100 adhesion promoter may be applied prior to application of the sealant in accordance with recommendations from the sealant manufacturer for specific substrates.

##### 1.3 Classification

###### 1.3.1 Types

- Type 1 - Sealing compound with a specific gravity of 1.20 to 1.35.
- Type 2 - Sealing compound with a specific gravity of 1.06 to 1.19.
- Type 3 - Sealing compound with a specific gravity of 1.05 or less.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2016 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)  
Tel: +1 724 776 4970 (outside USA)

**SAE values your input. To provide feedback on this Technical Report, please visit [standards/AMS3281E](http://standards/AMS3281E)**

This is a preview. Click here to purchase the full publication.

SAE WEB ADDRESS:

### 1.3.2 Classes

Class A - Suitable for application by brushing, injecting, or spraying. Available with the following application times in hours:

A-1/2  
A-2

Class B - Suitable for application by extrusion gun or spatula. Available with the following application times in hours:

B-1/2  
B-2

Class C - Suitable for faying surface or shim sealing, brush coating, or wet installation. Available with the following application times in hours:

Notation: ( ) Assembly time in hours.

C-2(2)  
C-8(24)  
C-12(48)  
C-48(168)  
C-96(336)

### 1.4 Safety - Hazardous Materials

Shall be in accordance with AS5502 (1.1).

## 2. APPLICABLE DOCUMENTS

Shall be in accordance with AS5502 (2).

### 2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), [www.sae.org](http://www.sae.org).

AMS2629	Fluid, Jet Reference
AMS3020	Oil, Reference, for "L" Stock Rubber Testing
AMS3021	Fluid, Reference, for Testing Di-ester (Polyol) Resistant Material
AMS3100	Adhesion Promoter, for Polysulfide Sealing Compounds
AMS4045	Aluminum Alloy Sheet and Plate, 5.6Zn - 2.5Mg - 1.6 Cu - 0.23 Cr, 7075: (-T6 Sheet, -T651 Plate), Solution and Precipitation Heat Treated
AMS4911	Titanium Alloy, Sheet, Strip, and Plate, 6Al - 4V, Annealed
AMS5516	Steel, Corrosion-Resistant, Sheet, Strip, and Plate, 18Cr - 9.0Ni (SAE 30302), Solution Heat Treated
AMS-C-27725	Coating, Corrosion Preventive, for Aircraft Integral Fuel Tanks for Use to 250 °F (121 °C)
AS5127	Aerospace Standard Test Methods for Aerospace Sealants Methods for Preparing Aerospace Sealants Test Specimens
AS5127/1	Aerospace Standard Test Methods for Aerospace Sealants, Two-Component Synthetic Rubber Compounds
AS5502	Standard Requirements for Aerospace Sealants and Adhesion Promoters

This is a preview. [Click here to purchase the full publication.](#)

## 2.2 U.S. Government Publications

Copies of these documents are available online at <http://quicksearch.dla.mil>.

MIL-PRF-23377 Primer Coatings: Epoxy Polyamide, High Solids

MIL-PRF-85285 Coating, Polyurethane, Aircraft and Support Equipment

MIL-PRF-85582 Primer Coatings, Epoxy, Waterborne

## 2.3 PRI Publications

Available from Performance Review Institute, 161 Thorn Hill Road, Warrendale, PA 15086-7527, Tel: 724-772-1616, [www.pri-network.org](http://www.pri-network.org).

PD2103 Aerospace Quality Assurance, Product Standards, Qualification Procedure, Sealants

PRI-QPL-AMS3281 Products Qualified Under AMS3281

## 3. TECHNICAL REQUIREMENTS

### 3.1 Materials

The basic ingredient shall be synthetic rubber, made from liquid polysulfide and derivations thereof. The sealing compound shall cure by the addition of a separate curing agent to the base compound and shall not depend on solvent evaporation for curing. The curing agent shall possess sufficient color contrast to the base compound to permit easy identification of an unmixed or incompletely mixed sealing compound. Neither the base compound nor the cured sealing compound shall be red or pink in color. No glass fillers shall be used.

### 3.2 Date of Packaging

Shall be in accordance with AS5502 (3.1).

### 3.3 Toxicological Formulations

Shall be in accordance with AS5502 (3.2).

### 3.4 Quality

Shall be in accordance with AS5502 (3.3).

### 3.5 Shelf Life

Shelf life shall be a minimum of 9 months from the date of packaging when stored below 80 °F. Material may be retested for shelf life extension per 4.3.3.

#### 3.5.1 Premixed and Frozen Material

Premixed and frozen material shall have a minimum storage life of 30 days at -40 °F (-40 °C) or lower, or 10 days at -10 to -40 °F (-23 to -40 °C) from date of mix/freeze. Recommendations for longer storage lives at lower temperatures may be provided by the manufacturer. The date of mix/freeze shall be within the shelf life of the unmixed material.

### 3.6 Properties

The base compound and the curing agent, when mixed in accordance with manufacturers' instructions and cured in accordance with 4.5.4.5, shall conform to the requirements shown in Table 1, when determined in accordance with the specified test methods.

**Table 1 - Properties**

Paragraph	Property	Requirement	Test Procedures (Paragraph)
3.6.1	Nonvolatile Content, by weight, min. Class A Class B Class C	85% 92% 85%	AS5127/1 (5.1)
3.6.2	Viscosity of Base Compound Class A (Use No. 6 spindle at 10 rpm) Class B (Use No. 7 spindle at 2 rpm) Class C (Use No. 6 spindle at 2 rpm)	100 to 500 poises (10 to 50 Pa•s) 7000 to 18000 poises (700 to 1800 Pa•s) 1000 to 4000 poises (100 to 400 Pa•s)	AS5127/1 (5.3)
3.6.3	Flow Class B, max.  Class C, min.	0.75 inches (19.0 mm)  0.010 inch (0.25 mm) If Tack-Free Time is not specified, measurement to be taken after Assembly Time	AS5127/1(5.5) AS5127/1 (5.5.1)  AS5127/1 (5.5.2)
3.6.4	Application Time, min. Class A - From the beginning of mixing, the viscosity shall not exceed 2500 poise (250 Pa•s), (Use No. 7 spindle at 10 rpm) A-1/2 A-2  Class B - From the beginning of mixing, not less than 15 grams per minute shall be extruded. B-1/2 B-2  Class C - From the beginning of mixing, not less than 30 grams per minute shall be extruded C-2(2) C-8(24) C-12(48) C-48(168) C-96(336)	1/2 hour 2 hours        2 hours 8 hours 12 hours 48 hours 96 hours	AS5127/1 (5.6) AS5127/1 (5.6.1)           AS5127/1 (5.6.2)           AS5127/1 (5.6.2)
3.6.5	Assembly Time, min. (Class C only) C-2(2) C-8(24) C-12(48) C-48(168) C-96(336)	2 hours 24 hours 48 hours 168 hours 336 hours	AS5127/1 (5.7)